

### **Listing of the Claims**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (currently amended) A catalyst composition for the polymerization of propylene or mixtures of propylene and one or more copolymerizable comonomers, said catalyst composition comprising one or more Ziegler-Natta procatalyst compositions comprising:

one or more transition metal compounds and one or more monoesters of aromatic carboxylic acid internal electron donors;

one or more aluminum containing ~~cocatalyst~~~~see catalysts~~; and

a mixture of two or more different selectivity control agents (SCA), said SCA mixture comprising from 98.5 98.0 to 99.9 mol percent of one or more esters of one or more aromatic monocarboxylic acids or substituted derivatives thereof, and from 1.5 ~~2.0~~ to 0.1 mol percent of one or more alkoxysilane compounds.

2. (original) The catalyst composition of claim 1 wherein the internal electron donor is ethyl benzoate.

3. (original) The catalyst composition of claim 1 wherein the SCA mixture comprises ethyl p-ethoxybenzoate and an alkoxysilane containing two or three methoxy groups.

4. (currently amended) The catalyst composition of ~~claim 1~~~~claim 3~~ wherein the alkoxysilane is dicyclopentyl dimethoxysilane or methylcyclohexyl dimethoxysilane.

5. (currently amended) A catalyst composition according to claim 1 wherein the total quantity of selectivity control agent employed ~~is limited to provide~~ provides a molar ratio, based on transition metal, from 1 to 100.

6. (currently amended) ~~The~~ A catalyst composition according to claim 1 ~~any one of claims 1-5~~ wherein the SCA mixture comprises from 98.5 to 99.5 mol percent of one or more alkyl

esters of one or more aromatic monocarboxylic acids or substituted derivatives thereof, and from 1.5 to 0.5 mol percent of one or more alkoxysilane compounds

7. (currently amended) A polymerization ~~method process~~ comprising:  
contacting propylene or a mixture of propylene and one or more copolymerizable comonomers under polymerization conditions at a temperature from 45 to 100 °C. with a catalyst composition comprising one or more Ziegler-Natta procatalyst compositions comprising one or more transition metal compounds and one or more internal electron donors selected from the group consisting of esters of aromatic monocarboxylic acids, one or more aluminum containing cocatalysts, and a mixture of two or more different selectivity control agents, said SCA mixture comprising from ~~98.5~~98.0 to 99.9 mol percent of one or more esters of one or more aromatic monocarboxylic acids or substituted derivatives thereof, and from ~~1.52~~1.0 to 0.1 mol percent of one or more alkoxysilane compounds.

8. (original) The method of claim 7 conducted at a temperature from 60 to 85 °C.

9. (original) The method of claim 7 wherein the internal electron donor is ethyl benzoate.

10. (original) The method of claim 7 wherein the SCA mixture comprises ethyl p-ethoxybenzoate and a dimethoxysilane.

11. (original) The method of claim 7 wherein the alkoxysilane is dicyclopentylmethoxysilane or methylcyclohexyldimethoxysilane.

12. (currently amended) The method according to claim 7 ~~any one of claims 7-11~~ conducted under gas phase polymerization conditions.

13. (currently amended) The method according to claim 7 ~~any one of claims 7-11~~ which is conducted in more than one reactor operating in series.

14. (new) The catalyst composition of claim 1 wherein the SCA mixture comprises from 98.6 to 99.0 mol percent of one or more alkyl esters of one or more aromatic monocarboxylic acids or substituted derivatives thereof, and from 1.4 to 1.0 mol percent of one or more alkoxy silane compounds.
15. (new) The composition of claim 1 wherein the alkoxy silane is selected from the group consisting of diisopropyldimethoxysilane, diisobutyldimethoxysilane, and isobutylisopropyldimethoxysilane.
16. (new) The catalyst composition of claim 1 wherein the SCA mixture comprises ethyl p-ethoxybenzoate and an alkoxy silane selected from the group consisting of dicyclopentyldimethoxysilane, methylcyclohexyldimethoxysilane, and n-propyltrimethoxysilane.
17. (new) The composition of claim 1 wherein the Ziegler-Natta procatalyst composition is a morphology controlled procatalyst.